

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
23 October 2003 (23.10.2003)

PCT

(10) International Publication Number  
**WO 03/087216 A1**

- (51) International Patent Classification<sup>7</sup>: C08L 23/04, 23/16 (74) Agents: KRIJGSMAN, Willem et al.; DSM Patents & Trademarks, P.O. Box 9, NL-6160 MA Geleen (NL).
- (21) International Application Number: PCT/NL03/00259 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 7 April 2003 (07.04.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 1020366 11 April 2002 (11.04.2002) NL (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant (*for all designated States except US*): DSM IP ASSETS B.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).
- (72) Inventors; and (75) Inventors/Applicants (*for US only*): BRULS, Wilhelmus, Gerardus, Marie [NL/NL]; Graaf Wolterhoenstraat 32, NL-6243 BE Geulle (NL). REPIN, Johannes, Fredericus [NL/NL]; Klingbenden 177, NL-6441 KX Brunssum (NL). WIDDERSHOVEN, Christian [NL/NL]; Sint Joosterweg 16 A, NL-6102 GB Echt (NL).
- Published:  
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: POLYMER COMPOSITION WITH IMPROVED TEMPERATURE RESISTANCE

(57) Abstract: Polymer composition, comprising as main components - a polyolefin polymer grafted with an ethylenically unsaturated functionalised compound with at least a first functional group; - a reactive thermoplastic polymer with a second functional group which can react with the first; and - a base polymer, comprising at least 55 wt% of a single site catalyst polymerised polyolefin, wherein the proportion of the base polymer amounts to more than 50 wt%, preferably to at least 55 wt% and the proportion of the reactive thermoplastic polymer to at least 10 wt% of the total of the main components, the proportion of the reactive thermoplastic polymer amounts to more than 50 wt% of the total of the reactive thermoplastic polymer and the polyolefin polymer grafted with an ethylenically unsaturated functionalised compound and the quantity of the ethylenically unsaturated functionalised compound in the grafted polyolefin polymer is between 0.05 and 1.0 mgeq/g, and a method for the preparation of such a composition.

WO 03/087216 A1

POLYMER COMPOSITION WITH IMPROVED TEMPERATURE RESISTANCE

5

The invention relates to a polymer composition, comprising as main components:

- a polyolefin polymer grafted with an ethylenically unsaturated functionalised compound with at least a first functional group;
- 10 - a reactive thermoplastic polymer with a second functional group which can react with the first functional group; and
- a base polymer.

Such a composition is known from WO-97/12919 as a mixture of the reaction product of the polyolefin polymer grafted with an ethylenically unsaturated functionalised compound and the reactive thermoplastic polymer with for example  
15 polypropylene as base polymer. The reaction product appears to have an improved temperature resistance, expressed in the 'Deflection temperature under load' according to ASTM standard D 648-82 at 66 psi, relative to the polyolefin polymer, and is applied as an impact modifier of the base polymer.

20 Objects, in particular layers, manufactured from the mixture obtained, when exposed to a temperature above the melting point of the base polymer appear to be subject to serious deformation and also to change in terms of appearance in an unfavourable sense.

The object of the invention is to provide a composition such as  
25 described in the opening lines hereof, which even upon exposure to temperatures above the melting point of the base polymer retain their shape and favourable appearance better.

This object is attained according to the invention in that the base polymer comprises at least 55 wt% of a single site catalyst polymerised polyolefin and  
30 in that the proportion of the base polymer amounts to more than 50 wt%, preferably to at least 55wt% and the proportion of the reactive thermoplastic polymer to at least 10 wt% of the total of the main components, in that the proportion of the reactive thermoplastic polymer amounts to at least 50 wt% of the total of the reactive thermoplastic polymer and the polyolefin polymer grafted with an ethylenically  
35 unsaturated functionalised compound and in that the quantity of the ethylenically unsaturated functionalised compound in the grafted polyolefin polymer is between 0.05

and 1.0 mgeq/g.

An object manufactured from the composition according to the invention appears upon exposure to a temperature above the melting point of the base polymer to retain its shape and favourable appearance longer than an object manufactured from the known composition. This is in particular the case when the melting point or the glass transition temperature of the reactive polymer is higher than that of the base polymer.

The polymer composition according to the invention contains a polyolefin polymer grafted with an ethylenically unsaturated functionalised compound, in the following referred to as 'grafted polyolefin polymer'.

As polyolefin polymers in the composition according to the invention are suitable homo- and copolymers of one or more olefin monomers that can be grafted with an ethylenically unsaturated functionalised compound. Examples of suitable polyolefin polymers are ethylene polymers, propylene polymers and styrene-butadiene-styrene block copolymers or the hydrogenated form hereof. Examples of suitable ethylene polymers are all thermoplastic homopolymers of ethylene and copolymers of ethylene with as comonomer one or more  $\alpha$ -olefins with 3-10 C-atoms, in particular propylene, isobutene, 1-butene, 1-hexene, 4-methyl-1-pentene and 1-octene which can be manufactured with the known catalysts such as for example Ziegler-Natta, Phillips and metallocene catalysts. The quantity of comonomer lies as a rule between 0 and 50 wt. %, and preferably between 5 and 35 wt. %. Such polyethylenes are for instance known as high-density polyethylene (HDPE), low-density polyethylene (LDPE), linear low-density polyethylene (LLDPE) and linear very low density polyethylene (VL(L)DPE). Suitable polyethylenes have a density between 860 and 970 kg/m<sup>3</sup>. Examples of suitable propylene polymers are homopolymers of propylene and copolymers of propylene with ethylene, in which the proportion of ethylene amounts to at most 30 wt% and preferably at most 25 wt%. Their Melt Flow Index (230°C, 2,16 kg) lies between 0.5 and 25 g/10min, more preferably between 1.0 and 10 g/10min.

Suitable ethylenically unsaturated functionalised compounds are those that can be grafted on at least one of the above-mentioned suitable polyolefin polymers. These compounds contain a carbon-carbon double bond and can form a side branch on a polyolefin polymer by grafting thereon. The compounds have been functionalised, which means that they possess a first functional group. Examples of functional groups are carboxylic acids and esters, anhydrides and salts thereof. The

functionalised compounds can also contain an epoxy ring, an amine group, an alkoxy silane group or an alcohol group. The compound can also be an ethylenically unsaturated oxazoline.


5        Examples of suitable ethylenically unsaturated functionalised compounds are the unsaturated carboxylic acids and esters and anhydrides and metallic or non-metallic salts thereof. Preferably the ethylenic unsaturation in the compound has been conjugated with a carbonyl group. Examples thereof are acrylic, methacrylic, maleic, fumaric, itaconic, crotonic, methyl crotonic, and cinnamic acid and esters, anhydrides and possible salts thereof. Of the compounds with at least one  
10        carbonyl group maleic anhydride is preferable.

      Examples of suitable ethylenically unsaturated functionalised compounds with at least one epoxy ring are for example glycidyl esters of unsaturated carboxylic acids, glycidyl ethers of unsaturated alcohols and of alkyl phenols and vinyl and allyl esters of epoxy carboxylic acids. Glycidyl methacrylate is specially suitable.

15        Examples of suitable ethylenically unsaturated functionalised compounds with at least one amine functionality are amine compounds with at least one ethylenically unsaturated group, for example allylamine, propenyl, butenyl, pentenyl and hexenyl amine, amine ethers, for example isopropenylphenyl ethylamine ether. The amine group and the unsaturation should be situated relative to each other  
20        in such a position that they do not influence the grafting reaction to an undesirable degree. The amines can be unsubstituted but also substituted with for example alkyl and aryl groups, halogen, ether and thioether groups.

      Examples of suitable ethylenically unsaturated functionalised compounds with at least one alcohol functionality are all compounds with a hydroxyl  
25        group whether or not etherified or esterified and an ethylenically unsaturated compound, for example allyl and vinyl ethers of alcohols such as ethyl alcohol and higher branched and unbranched alkyl alcohols, as well as allyl and vinyl esters of alcohol-substituted acids, preferably carboxylic acids and C<sub>3</sub>-C<sub>3</sub>-C<sub>8</sub> alkenyl alcohols. The alcohols can further be substituted with for example alkyl and aryl groups, halogen,  
30        ether and thioether groups which do not influence the grafting reaction to an undesirable degree.

      Examples of oxazoline compounds that are suitable as ethylenically unsaturated functionalised compounds in the framework of the invention are for example those with the following general formula



wherein each R independently of the other hydrogen, is a halogen, a C<sub>1</sub>-C<sub>10</sub> alkyl  
 5 radical or a C<sub>6</sub>-C<sub>14</sub> aryl radical.

The quantity of the ethylenically unsaturated functionalised compound in the grafted polyolefin polymer lies between 0.05 and 1 mgeq per gram polyolefin polymer. It was found that with quantities above the indicated upper limit the compatibilising effect of the grafted polyolefin polymer decreases and that with  
 10 quantities below the lower limit the intended effect of the reactive polymer decreases. Said quantities correspond to an average molecule part between two grafting sites which is equivalent to a molecular weight situated between 1000 and 20000. Preferably the quantity of the ethylenically unsaturated functionalised compound in the grafted polyolefin polymer lies between 0.1 and 0.5 mgeq per gram polyolefin polymer and  
 15 more preferably between 0.15 and 0.3 mgeq per gram polyolefin polymer. The grafted polyolefin polymer can be prepared by reacting the polyolefin polymer with the ethylenically unsaturated functionalised compound according to methods known per se for this purpose, for example as described in US patent 3,236,917, US patent 5,194,509 and US patent 4,950,541.

20 The composition according to the invention further contains a reactive thermoplastic polymer, hereafter also referred to as reactive polymer. Suitable reactive thermoplastic polymers are semi-crystalline or amorphous polymers that contain a second functional group which can react in the melt with the first functional group of the ethylenically unsaturated functionalised compound that has been grafted on the  
 25 polyolefin polymer. The melting point or the glass transition point, respectively, of the semi-crystalline or the amorphous polymers preferably lies above 120°C or above 100°C, respectively, and more preferably above 150°C or above 120°C, respectively. Suitable second functional groups are for example hydroxy, phenolic, (carboxylic) acid (anhydride), amine, epoxy and isocyanate groups. Examples of suitable reactive  
 30 thermoplastic polymers are polybutylene terephthalate (PBT), polyethylene terephthalate (PET), amine-functionalised polymers including semi-crystalline

polyamides, for example polyamide-6, polyamide-66, polyamide-46 and amorphous polyamides, for example polyamide-6I or polyamide-6T, polysulfon, polycarbonate, epoxy-functionalised polymethyl acrylate, styrene-acrylonitrile functionalised with epoxy or other functional groups as mentioned above. Suitable reactive polymers are those with the common intrinsic viscosities and molecular weights. For polyesters the intrinsic viscosity lies for example between 1.8 and 2.5 dl/g, measured in m-cresol at 25°C. For polyamides the molecular weight lies for example between 10000 and 50000 and preferably between 15000 and 30000.

Polyamides are very suitable due to their availability across a wide range of melting points. Also, the reaction of their second reactive group with for example the MZA-grafted polymers advantageously applied as graft polymer is irreversible under the circumstances under which the compositions are as a rule applied.

The first and the second functional group of the functionalised ethylenically unsaturated compound or of the reactive polymer, respectively, are chosen in such a way that both functionalities can react mutually so that the reactive polymer and the ethylenically unsaturated compound can bind with each other.

The proportion of the reactive polymer in the total of the reactive polymer and the grafted polyolefin polymer amounts to at least 50 wt% and more preferably at least 60 and preferably at most 95 wt% and more preferably at most 85 wt%. The two functionalised components in the composition according to the invention occur therein in whole or in part in the form of the compound formed through the mutual reaction of the respective functional groups. The specified quantities of these components always relate to the quantities reduced to unreacted starting components. The composition can also be defined as being formed from the three main components.

The polymer composition according to the invention contains a base polymer, comprising at least 55 wt% of a single site catalyst polymerised polyolefin. Examples of single site catalysts are metallocene catalysts. The polyolefins preferably as their main component comprise ethylene or propylene. Polyolefins that in particular benefit from the advantages of the present invention are copolymers of ethylene with for example 1-butene, 1-hexene or 1-octene, manufactured with a metallocene catalyst, referred to herein as 'plastomers'. A composition in which plastomers such as polyolefin polymers occur appear to possess both a good resistance to exposure to

temperatures above the melting point of the base polymer and a high flexibility even at lower temperatures. Preferably the plastomer has a density of at most  $910 \text{ kg/m}^3$ , more preferably of at most  $890 \text{ kg/m}^3$  and most preferably at most  $885 \text{ kg/m}^3$ . The single site catalyst polymerised polyolefin should form a continuous matrix phase in the base polymer. In addition to the single site catalyst polymerised polyolefins the base polymer may comprise other polymers, in particular polyolefins. These polyolefins can be polymerised with conventional polymerisation techniques with Ziegler-Natta or Phillips type catalysts. Furthermore the base polymer may comprise polystyrene, acryl-butadiene-styrene, ethylene vinyl alcohol, polyvinyl alcohol, polyvinylchloride, polyurethane, polycarbonate and SEBS, SBR and EP(D)M rubbers. The total amount of other polymers than the single site catalysed polyolefins in the base polymer may range from 0 to 45 wt.%. Mixtures of the reaction product and mutually compatible base polymers can also be applied. Preferably besides the single site catalyst polymerised polyolefins at least polyethylene is comprised in the base polymer.

In order to ensure that the properties of the base polymer are present to a sufficient degree in the composition the base polymer should form a continuous phase in the composition. The proportion of the base polymer therefore is at least 50 wt%, preferably 55 wt% and more preferably at least 70%. The proportion of the two other main components then amounts to at most 45 or 30 wt%.

The proportion of the reactive polymer amounts to at least 10 wt% of the total of the main components. Lower quantities appear to contribute only in small measure to the improvement of the resistance to exposure to elevated temperatures. The achievable improvement of the resistance to exposure to a temperature above the melting point of the base polymer is determined especially by the difference in melt temperature between the reactive polymer and the base polymer. The melt temperature of the reactive polymer is therefore preferably higher than that of the base polymer and that of the polyolefin polymer, in particular at least  $10^\circ\text{C}$  and preferably at least  $20^\circ\text{C}$  higher.

In addition to the above-mentioned three main components the composition according to the invention can optionally contain the commonly used additives for such polymer compositions, for example stabilisers, colorants, processing auxiliaries, release agents, flame-retardant additives and fillers or reinforcing fibre (materials).

The compositions according to the invention can be applied

advantageously where for processing into a moulded article and/or the use thereof a combination of dimensional stability at higher temperatures and the specific properties, in particular the flexibility, of the base polymer, are required. Examples thereof are films and sheets, hoses, conveyor belts, bellows and blow-moulded articles.

5                   The invention also relates to a method for preparation of a polymer composition at least comprising as main components:

- a polyolefin polymer grafted with an ethylenically unsaturated functionalised compound with at least a first functional group;
- a reactive thermoplastic polymer with a second functional group which can react  
10                   with the first; and
- a base polymer comprising at least 55 wt% of a single site catalyst polymerised polyolefin.

Such a method is known from WO 97/12919, where first a reaction product is prepared, for example by reactive extrusion, of the polyolefin polymer with  
15                   the reactive thermoplastic polymer, with the respective functional groups reacting with each other. Subsequently the resulting reaction product is mixed in the melt with the base polymer.

The known method presents the disadvantage that objects manufactured from the finally obtained composition appear to deform seriously upon  
20                   exposure to a temperature above the melting point of the polyolefin polymer and to change in terms of appearance in an unfavourable sense.

The aim of the invention is to provide a method with which a composition can be manufactured from the said components and which does not exhibit this disadvantage or exhibits it to a significantly less degree.

25                   This object is attained according to the invention in that the base polymer and the polyolefin polymer, grafted with the ethylenically unsaturated functionalised compound in an amount of between 0.05 and 1.0 mgeq/g, are mixed with each other in the molten state, after which the resulting molten mixture is mixed in the melt with the reactive thermoplastic polymer, the proportion of the base polymer  
30                   amounting to more than 50, preferably to at least 55 wt% and the proportion of the reactive thermoplastic polymer to at least 10 wt% of the total of the main components and the proportion of the reactive thermoplastic polymer amounts to at least 50 wt% of the total of the reactive thermoplastic polymer and the polyolefin polymer grafted with an ethylenically unsaturated functionalised compound.

35                   Surprisingly, mixing of the three main components in said and in



accordance with said specifications appears to yield a composition with a better resistance to exposure to temperatures above the melting point of the base polymer than the known process, which consists of first reacting the grafted polyolefin polymer with the reactive polymer and subsequent combining of the resulting reaction product and the base polymer.

5 If the melting point of the reactive polymer is higher than that of the other two main components the mixing of the three said main components can be carried out by feeding three main components together to for example an extruder. Due to the difference in melting point between the polyolefin polymer and the base polymer on the one hand and the higher melting point of the reactive polymer on the other hand the two first-mentioned components will melt first and will be mixed in the extruder in the molten state. The reactive polymer is then still in the solid state. Upon further heating of the components in the extruder the reactive polymer will also melt and then mix with the already present mixture to form an end mixture in which all three components have been mixed with each other. During this second mixing phase the reactive polymer reacts with the grafted ethylenically unsaturated polymer. It was found that in the method according to the invention the specific choice of the quantity of functional groups makes the application of catalysts superfluous. In the method according to the invention therefore preferably no catalysts are applied to promote the reaction between the reactive polymer and the grafted polyolefin polymer. The difference in the timing of the melting of the different components can be influenced in a way known to the person skilled in the art by means of the extruder temperature and its course and the forces exerted on the mixture in the extruder, for example shear forces.

25 In a second embodiment of the method according to the invention first the base polymer and the grafted polyolefin polymer are mixed with each other, for example in an extruder, in the molten state, after which the reactive polymer is mixed in further upstream in the extruder in or in an additional extrusion step.

For the mixing in the melt phase the current techniques and apparatus known to the person skilled in the art can be applied. Particularly suitable for preparation of the composition is for example a co-rotating twin-screw extruder. Preferably the mixing is carried out in the melt in an inert gas atmosphere.

While mixing in the melt takes place, the customary additives and auxiliary agents for polymer compositions, besides the above-mentioned catalysts, can be added, for example stabilisers, colorants, processing auxiliaries, release agents,

flame-retardant additives and fillers or reinforcing fibre (materials). Suitable main components that can be applied in the method according to the invention and their proportions are those as described above for the composition according to the invention.

5                   The invention will be elucidated on the basis of the following examples without being restricted thereto.

Examples I-III and comparative experiment A

The following materials were used:

- 10   Exact® 8201:           ethylene octene copolymer (plastomer) from DEX Plastomers,  
                                  density 882 kg/m<sup>3</sup>, MFI = 1 dg/min;
- Exact®-g-MZA (1):   ethylene octene copolymer grafted with 1.5 wt% maleic  
                                  anhydride;
- Exact®-g-MZA (2):   ethylene octene copolymer grafted with 0.6 wt% maleic  
15                               anhydride;
- Akulon® K122:       polyamide-6, intrinsic viscosity 2.2 (determined at 25°C in  
                                  formic acid), from DSM;
- HDPE-g-MZA         ethylene homopolymer with a density of 962 kg/m<sup>3</sup>, grafted with  
                                  1.8 wt% maleic anhydride.

20

Three solid mixtures were prepared by mixing in the solid state in a  
tumbler of the quantities of the raw materials stated in Table 1. The resulting solid  
mixtures were metered with the aid of a K-tron metering unit via the throat to a ZSK 30  
mm twin-screw extruder and in this extruder, by melting and mixing with a throughput  
25   of 5 kg/hour, a speed of 200 rpm and a temperature profile of 150-260°C, converted  
into three compositions, I II and III, by the method according to the invention.  
Composition A was prepared according to the known method by first mixing the  
reactive polymer Akulon K122 in the melt with the grafted polyolefin polymer and  
subsequently mixing the resulting reacted mixture in the melt with the base polymer.

30

Table 1

Composition (wt. %)	I	II	III	A
Exact® 8201 (base polymer)	75	50	50	50
Exact MZA 1	5	10		
Exact MZA 2				30
HDPE-g-MZA			10	
Akulon® K122	20	40	40	20

Injection moulding of test specimens

5 For the production of test specimens in the form of test bars with a length of 70 mm, a width of 10 mm and a thickness of 1 mm the compositions obtained from the extruder, after predrying for 24 hours in a vacuum furnace at 50°C, were injection-moulded with application of an extruder temperature profile of 240°C -275°C, resulting in a temperature of the melt of 250°C ±5°C, a speed of 200 rpm, a thrust of 7,5 mPa and a mould temperature of 50°C.

10 The test specimens were supported on the topsides of the 20 mm high upright edges of an aluminium U-profile with a spacing of 50 mm. The profile with the supported test specimens was placed in a hot-air furnace which was then brought to a temperature of 150°C and afterwards kept at that temperature. After 30 minutes the test bar made from composition A appeared to have already sagged to the bottom of the U-profile and was partly necked in the width. Its surface showed bumps.

15 The test bar made from composition I appeared to have sagged a little in the middle, approximately 5 mm, only after 60 minutes. Its width had remained almost equal over the whole length of the rod. Its surface was still virtually smooth.

20 The test specimens made from compositions II and III hardly showed any sagging or change in width even after 60 minutes. Their surface was still flat and smooth.

CLAIMS

1. Polymer composition, comprising as main components
  - 5 - a polyolefin polymer grafted with an ethylenically unsaturated functionalised compound with at least a first functional group;
  - a reactive thermoplastic polymer with a second functional group which can react with the first; and
  - 10 - a base polymer comprising at least 55 wt% of a single site catalyst polymerised polyolefin,wherein the proportion of the base polymer amounts to more than 50, preferably to at least 55 wt% and the proportion of the reactive thermoplastic polymer to at least 10 wt% of the total of the main components, and wherein the proportion of the reactive thermoplastic polymer amounts to more than 50  
15 wt% of the total of the reactive thermoplastic polymer and the polyolefin polymer grafted with an ethylenically unsaturated functionalised compound and wherein the quantity of the ethylenically unsaturated functionalised compound in the grafted polyolefin polymer is between 0.05 and 1.0 mgeq/g.
2. Polymer composition according to claim 1, in which the base polymer is  
20 polyethylene.
4. Polymer composition according to any one of claims 1-3, in which the reactive polymer is a polyamide.
5. Method for preparation of a polymer composition at least comprising as main components
  - 25 - a polyolefin polymer grafted with an ethylenically unsaturated functionalised compound with at least a first functional group;
  - a reactive thermoplastic polymer with a second functional group which can react with the first; and
  - a base polymer,characterised in that the base polymer comprises at least 55 wt% of a single  
30 site catalyst polymerised polyolefin, and in that the base polymer and the polyolefin polymer, grafted with the ethylenically unsaturated functionalised compound in an amount of between 0.05 and 1.0 mgeq/g, are mixed with each other in the molten state, after which the resulting molten mixture is  
35 mixed in the melt with the reactive thermoplastic polymer, the proportion of the

5 base polymer amounting to more than 50 wt%, preferably to at least 55 wt% and the proportion of the reactive thermoplastic polymer to at least 10 wt% of the total of the main components and the proportion of the reactive thermoplastic polymer amounts to more than 50 wt% of the total of the reactive thermoplastic polymer and the polyolefin polymer grafted with an ethylenically unsaturated functionalised compound.

## INTERNATIONAL SEARCH REPORT

PCT/NL 03/00259

**A. CLASSIFICATION OF SUBJECT MATTER**  
 IPC 7 C08L23/04 C08L23/16

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
 IPC 7 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

PAJ, EPO-Internal, WPI Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 77078 A (REPIN JOHANNES FREDERICUS ;DSM NV (NL); KROON JAN DE (NL); BRULS W) 21 December 2000 (2000-12-21) abstract; claims 1-16 page 1, line 8-12 page 4, line 15-27 page 5, line 5-8,20-33 page 6, line 11-29 page 7, line 6-30	1-4
X	EP 0 866 081 A (KANEGAFUCHI CHEMICAL IND) 23 September 1998 (1998-09-23) abstract; claims 1-33 page 4, line 43-60 page 6, line 18,35 page 7, line 4,11,21,54 page 8, line 4,10,56-60 page 9, line 6,21-39	1-4
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

25 June 2003

Date of mailing of the international search report

03/07/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
 Fax: (+31-70) 340-3018

Authorized officer

Bergmans, K

# INTERNATIONAL SEARCH REPORT

PCT/NL 03/00259

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>US 6 117 561 A (CORBIC-BELLINGER MARIE-PIERRE ET AL) 12 September 2000 (2000-09-12) abstract; claims 1-39 column 3, line 30,58-62 column 5, line 13</p>	1-3

## INTERNATIONAL SEARCH REPORT

PCT/NL 03/00259

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0077078	A	21-12-2000	NL 1012324 C2	15-12-2000
			AT 234887 T	15-04-2003
			AU 4956700 A	02-01-2001
			CN 1355823 T	26-06-2002
			DE 60001740 D1	24-04-2003
			EP 1185578 A1	13-03-2002
			JP 2003502464 T	21-01-2003
			WO 0077078 A1	21-12-2000
			US 2002156191 A1	24-10-2002
EP 0866081	A	23-09-1998	JP 9157335 A	17-06-1997
			JP 9176478 A	08-07-1997
			EP 0866081 A1	23-09-1998
			WO 9721745 A1	19-06-1997
US 6117561	A	12-09-2000	FR 2740381 A1	30-04-1997
			AU 7309096 A	15-05-1997
			CA 2208980 A1	01-05-1997
			CN 1175968 A	11-03-1998
			EP 0800552 A1	15-10-1997
			WO 9715621 A1	01-05-1997
			JP 2000509076 T	18-07-2000
			KR 262418 B1	01-08-2000
			NO 972823 A	18-06-1997
			ZA 9609044 A	03-07-1998